

TECHNICAL DATA SHEET

CODE: HFI 01_29072021

NAME: HFI 01_29072021 - WB PARKETT SEALER 1K/2K FOR ROLLER APPLICATION

GROUP: WATER-BASED SINGLE/BICOMPONENT TRANSPARENT PRIMER

CHARACTERISTICS

Water-based single/bicomponent transparent antiyellowing primer, to apply by roller, to be used to obtain a natural timber effect on parquet.

TECHNICAL SPECIFICATIONS

HFI 01_2907 2021 12032019	Property	Specification	Units	Method
	Density (20°C)	0,98 - 1,08	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	20 - 30	Sec.	IST 11/08
	Solid Content	20 - 24	%	IST 11/06
CVP 02_290 72021	Property	Specification	Units	Method
	Density (20°C)	1,09 - 1,19	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	50 - 60	Sec.	IST 11/08
	Solid Content	68,0 - 72,0	%	IST 11/06

The values describe the typical properties of the product. Technical Specifications are available upon request.

USE

It is recommended to stir well the product before use.

The product is ready for use, if necessary thin it with water. The dilution of the product is determined at the time of application depending on the application parameters present, recommended at 10% by weight. It is recommended to mix well after addition. To further improve the final chemical and mechanical characteristics of the product, it is possible to harden the product with the hardener CVP 02_29072021 at 10% by weight. Stirr the product well after addition of the pigment pastes.

The product has been developed to be applied by roller, in alternativa è possibile applicare il prodotto con pistole a spruzzo aventi un ugello da 1,6 a 2,0 millimetri e con una pressione da 2,0 a 3,0 bar.

For optimal results, product application and drying should happend at higher temperature than 15°C and humidity lower than 80%.

APPLICATION

Recommended amount for single coat	80 - 100 gr/m ² (recommended)
Touch-free	About 1h at 20°C (with good ventilation)
Number of coats	up to a maximum of 2 coats
Time before to apply the seconds coat.	After 2 - 4 hours at 20°C (with good ventilation)
Time before the sanding, for a single coat	After 3 - 4 hours at 20°C (with good ventilation)
Time before the sanding, with a double coats	After 8 - 12 hours at 20°C (with good ventilation)
Stacking	24h at 20°C (with good ventilation)

MOD. 12 - 08 (Rev. 2 - 02/2026)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. SERVIND ITALY reserves the right to introduce technical changes without prior notice.

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between + 5°C and + 35°C) that is not subject to abrupt temperature excursions. Standard packaging size of 25 Kg; for other requests a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 12 - 08 (Rev. 2 - 02/2026)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. SERVIND ITALY reserves the right to introduce technical changes without prior notice.