

TECHNICAL DATA SHEET

CODE: VES0358

NAME: VES0358 - SOFT-TOUCH - 2G

GROUP: Special Effects

CHARACTERISTICS

Dual component solvent based topcoat based on urethane resins, for regular and electrostatic spray application on wood, or over pigmented solvent-based two-component acrylic/polyurethane finishes characterized by the typical rubber effect, soft to the touch, but with good scratch resistance. Intended for interior applications.

TECHNICAL SPECIFICATIONS

VES0358	Property	Specification	Units	Method
	Density (20°C)	0,9-1,0	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	28-38	Sec.	IST 11/08
	Solid Content	30-34	%	IST 11/06
CVP0247	Property	Specification	Units	Method
	Density (20°C)	0,96 - 1,00	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	08 - 10	Sec.	IST 11/08
	Solid Content	27 - 31	%	IST 11/06

The values describe the typical properties of the product. Technical Specifications are available upon request.

USE

Harden VES0358 at 50% by weight with CVP0247, subsequently thin it with DPV0006. The thinning of the product is established at the time of application according to the application parameters present, recommended at 20% by weight. It is recommended to stir well the product after the thinning.

During application, the temperature of components should not be less than 18°C.

To get the best performance in terms of design and adhesion, the interaction with other supporting products is of the utmost importance, please contact our technical service.

APPLICATION

Pot-Life	About 3 hours at 20°C (with good ventilation)
Recommended quantity	80 - 100 gr/m ² (one single coat only)
Application with spray gun.	Nozzle size 1,0 - 1,3 mm - Pressure 2,0 - 2,5 bar
Application by Airmix System	Nozzle diameter 0.23 - 0.28 mm - Pressure 60- 100 bar, Atomizer pressure 2.0 - 2.5 bar

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between + 4°C and + 30°C) that is not subject to abrupt temperature excursions. Standard packaging size of 5 Kg; for other requests a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 12 - 08 (Rev. 2 - 02/2026)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. SERVIND ITALY reserves the right to introduce technical changes without prior notice.