TECHNICAL DATA SHEET



Name: UPT Series - TREPPENLACKE
Code: UPT Series
Identification: STAIR PAINT
Revision: Rev.2 - 11/2026

Features

Solvent-based clear multilayer paint, for application with spray, brush and roller, characterised by a high resistance to mechanical stresses. Specifically intended for painting interior stairs, available in two opacity levels: 80 and 25 Gloss.

Technical Specifications

UPT Series	Property	Specification	Unit	Method
	Density (20°C)	0,97 - 1,02	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	54 - 66	Sec.	IST 11/08
	Solid Content	42 - 47	%	IST 11/06
CVP0218	**Property**	**Specification**	**Unit**	**Method**
	Density (20°C)	0,89 - 0,93	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	09 - 11	Sec.	IST 11/08
	Solid Content	23 - 27	%	IST 11/06
CVP0219	**Property**	**Specification**	**Unit**	**Method**
	Density (20°C)	0,96 - 1,00	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	09 - 11	Sec.	IST 11/08
	Solid Content	23 - 27	%	IST 11/06

The values describe the typical properties of the product. Technical Specifications are available upon request.

Use

Harden the product at 100% by weight with the hardener CVP0219, subsequently thin it with DPV0006. The thinning of the product is established at the time of application according to the application parameters present, recommended at 10% by weight. In the summer season and in the presence of high temperatures, it is recommended to use the CVP0218 always at 100% by weight, as an alternative to the CVP0219, to allow a good distension of the product.

Application methods

Dipping	☐	Spraying	☑	Roller	☑	Brush	☑
Cloth	☐	Spatula	☐	Flow-coating	☐		

TECHNICAL DATA SHEET



Name: UPT Series - TREPPENLACKE
Code: UPT Series
Identification: STAIR PAINT
Revision: Rev.2 - 11/2026

Application

	Pot-Life	About 2 - 3 hours at 20°C (with good ventilation)
	Suggested amount	90 - 120 Gr/m²
	Dust free	About 20' - 25' at 20°C (with good ventilation)
	Touch-free	About 60' - 50' at 20°C (with good ventilation)
	Sanding	After 2 hours at 20°C (with good ventilation)
	Stacking	After 24 hours at 20°C (with good ventilation)

Storage and packaging

Keep it tightly sealed in its original container in a cool environment (between - 5°C and + 40°C) that is not subject to abrupt temperature excursions. Standard packaging size of 25 Kg; for other requests a feasibility evaluation will be made.

Safety precautions

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 10 - 26
The data shown refer to laboratory tests; in practical applications they may vary significantly depending on the application conditions. The user must in any case verify the suitability of the product for the intended use and assumes all responsibility arising from its use. SERVIND ITALY reserves the right to make technical changes without prior notice.

SERVIND ITALY s.r.l. - Via Palmanova 62/1 - 33048 San Giovanni al natisone - (UD) ITALY - Phone: +39 0432 756261 - Fax +39 0432 756630 - info@servind.it - www.servind.it