TECHNICAL DATA SHEET



Name: VES0235 FINITURA METALIZZATA MONOCOMP.
Code: VES0235
Identification: FINITURA METALI
Revision: Rev.1 - 11/2026

Features

Single-component, solvent-based paint, applicable by normal or electrostatic spraying, on wood and wood-based materials, and on metal, plastic and MDF after the use of appropriate primers, giving the surface a matt aluminium-like appearance. Highly resistant to scratches, wear and thermal shock, according to the products used as topcoat.

Technical Specifications

VES0235	Property	Specification	Unit	Method
	Density (20°C)	0,94 - 0,98	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	140 - 160	Sec.	IST 11/08
	Solid Content	26 - 30	%	IST 11/06

The values describe the typical properties of the product. Technical Specifications are available upon request.

Use

Thin the Product with DPV0006. The thinning of the product is established at the time of application according to the application parameters present, recommended at 50% by weight.
When a better product spreading is required, it is recommended to add a small amount of retardant thinner DPV0026 to the mix.
Apply two coats of product with an interval of about 3 - 5 minutes.

Application methods

Dipping ☐ Spraying ☐ Roller ☐ Brush ☐
Cloth ☐ Spatula ☐ Flow-coating ☐

Application

	Suggested amount	90 - 120 gr/m²
	Dust free	About 15' at 20°C (with good ventilation)
	Overcoating interval	From a minimum of 20' to a maximum of 6 hours
	Stacking	After about 24 hours at 20°C (with good ventilation)

Storage and packaging

Keep it tightly sealed in its original container in a cool environment (between + 4°C and + 30°C) that is not subject to abrupt temperature excursions.
Standard confection of 25 kg. For other specific requests, a feasibility assessment will be carried out.

TECHNICAL DATA SHEET



Name: VES0235 FINITURA METALIZZATA MONOCOMP.
Code: VES0235
Identification: FINITURA METALI
Revision: Rev.1 - 11/2026

Safety precautions

The product is intended for professional use only, refer to the Safety Data Sheet.

The data shown refer to laboratory tests; in practical applications they may vary significantly depending on the application conditions. The user must in any case verify the suitability of the product for the intended use and assumes all responsibility arising from its use. SERVIND ITALY reserves the right to make technical changes without prior notice.

SERVIND ITALY s.r.l. - Via Palmanova 62/1 - 33048 San Giovanni al natisone - (UD) ITALY - Phone: +39 0432 756261 - Fax +39 0432 756630 - info@servind.it - www.servind.it